

IN THE CLAIMS:

Please enter the following claim set:

1. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;
- a gate electrode formed on the gate dielectric film; and
- a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,

wherein, when a power supply voltage of 0.6 V is used,

- a thickness of the SOI film is 0.084 μm or greater and 0.094 μm or smaller, and an

B' impurity concentration of the SOI film is $7.95 \times 10^{17}/\text{cm}^3$ or greater and $8.05 \times 10^{17}/\text{cm}^3$ or smaller.

2. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;
- a gate electrode formed on the gate dielectric film; and
- a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,

wherein, when a power supply voltage of 0.6 V is used,

- a thickness of the SOI film is 0.089 μm or greater and 0.099 μm or smaller, and an

impurity concentration of the SOI film is $8.95 \times 10^{17}/\text{cm}^3$ or greater and $9.05 \times 10^{17}/\text{cm}^3$ or smaller.

3. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;
- a gate electrode formed on the gate dielectric film; and
- a diffusion layer for source/drain regions formed in source/drain regions of the SOI film, wherein, when a power supply voltage of 0.6 V is used,
- a thickness of the SOI film is 0.093 μm or greater and 0.103 μm or smaller, and an impurity concentration of the SOI film is $0.095 \times 10^{18}/\text{cm}^3$ or greater and $1.005 \times 10^{18}/\text{cm}^3$ or smaller.

B.I
cont'd

4. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;
- a gate electrode formed on the gate dielectric film; and
- a diffusion layer for source/drain regions formed in source/drain regions of the SOI film, wherein, when a power supply voltage of 0.6 V is used,
- a thickness of the SOI film is 0.096 μm or greater and 0.106 μm or smaller, and an impurity concentration of the SOI film is $1.095 \times 10^{18}/\text{cm}^3$ or greater and $1.105 \times 10^{18}/\text{cm}^3$ or smaller.

5. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;

a gate electrode formed on the gate dielectric film; and
 a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
 wherein, when a power supply voltage of 0.6 V is used,
 a thickness of the SOI film is 0.100 μm or greater and 0.110 μm or smaller, and an
 impurity concentration of the SOI film is $1.195 \times 10^{18}/\text{cm}^3$ or greater and $1.205 \times 10^{18}/\text{cm}^3$ or
 smaller.

6. (original) A semiconductor device to be used for a CMOS inverter circuit, the
 semiconductor device comprising:

B1
contd

a dielectric film formed on a semiconductor substrate;
 a SOI film comprising single crystal Si formed on the dielectric layer film;
 a gate dielectric film formed on the SOI film;
 a gate electrode formed on the gate dielectric film; and
 a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
 wherein, when a power supply voltage of 0.8 V is used,
 a thickness of the SOI film is 0.068 μm or greater and 0.078 μm or smaller, and an
 impurity concentration of the SOI film is $7.95 \times 10^{17}/\text{cm}^3$ or greater and $8.05 \times 10^{17}/\text{cm}^3$ or
 smaller.

7. (original) A semiconductor device to be used for a CMOS inverter circuit, the
 semiconductor device comprising:

a dielectric film formed on a semiconductor substrate;
 a SOI film comprising single crystal Si formed on the dielectric layer film;
 a gate dielectric film formed on the SOI film;
 a gate electrode formed on the gate dielectric film; and
 a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
 wherein, when a power supply voltage of 0.8 V is used,

a thickness of the SOI film is $0.074\text{ }\mu\text{m}$ or greater and $0.084\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $8.95 \times 10^{17}/\text{cm}^3$ or greater and $9.05 \times 10^{17}/\text{cm}^3$ or smaller.

8. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

a dielectric film formed on a semiconductor substrate;

a SOI film comprising single crystal Si formed on the dielectric layer film;

a gate dielectric film formed on the SOI film;

a gate electrode formed on the gate dielectric film; and

a diffusion layer for source/drain regions formed in source/drain regions of the SOI film, wherein, when a power supply voltage of 0.8 V is used,

a thickness of the SOI film is $0.078\text{ }\mu\text{m}$ or greater and $0.088\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $0.095 \times 10^{18}/\text{cm}^3$ or greater and $1.005 \times 10^{18}/\text{cm}^3$ or smaller.

9. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

a dielectric film formed on a semiconductor substrate;

a SOI film comprising single crystal Si formed on the dielectric layer film;

a gate dielectric film formed on the SOI film;

a gate electrode formed on the gate dielectric film; and

a diffusion layer for source/drain regions formed in source/drain regions of the SOI film, wherein, when a power supply voltage of 0.8 V is used,

a thickness of the SOI film is $0.083\text{ }\mu\text{m}$ or greater and $0.093\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $1.095 \times 10^{18}/\text{cm}^3$ or greater and $1.105 \times 10^{18}/\text{cm}^3$ or smaller.

10. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;
- a gate electrode formed on the gate dielectric film; and
- a diffusion layer for source/drain regions formed in source/drain regions of the SOI film, wherein, when a power supply voltage of 0.8 V is used, a thickness of the SOI film is $0.087\text{ }\mu\text{m}$ or greater and $0.097\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $1.195 \times 10^{18}/\text{cm}^3$ or greater and $1.205 \times 10^{18}/\text{cm}^3$ or smaller.

B.1
cont'd

11. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;
- a gate dielectric film formed on the SOI film;
- a gate electrode formed on the gate dielectric film; and
- a diffusion layer for source/drain regions formed in source/drain regions of the SOI film, wherein, when a power supply voltage of 1.0 V is used, a thickness of the SOI film is $0.057\text{ }\mu\text{m}$ or greater and $0.067\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $7.95 \times 10^{17}/\text{cm}^3$ or greater and $8.05 \times 10^{17}/\text{cm}^3$ or smaller.

12. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
- a SOI film comprising single crystal Si formed on the dielectric layer film;

a gate dielectric film formed on the SOI film;
 a gate electrode formed on the gate dielectric film; and
 a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
 wherein, when a power supply voltage of 1.0 V is used,
 a thickness of the SOI film is 0.063 μm or greater and 0.073 μm or smaller, and an
 impurity concentration of the SOI film is $8.95 \times 10^{17}/\text{cm}^3$ or greater and $9.05 \times 10^{17}/\text{cm}^3$ or
 smaller.

13. (original) A semiconductor device to be used for a CMOS inverter circuit, the
 semiconductor device comprising:

B' contd

a dielectric film formed on a semiconductor substrate;
 a SOI film comprising single crystal Si formed on the dielectric layer film;
 a gate dielectric film formed on the SOI film;
 a gate electrode formed on the gate dielectric film; and
 a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
 wherein, when a power supply voltage of 1.0 V is used,
 a thickness of the SOI film is 0.068 μm or greater and 0.078 μm or smaller, and an
 impurity concentration of the SOI film is $0.095 \times 10^{18}/\text{cm}^3$ or greater and $1.005 \times 10^{18}/\text{cm}^3$ or
 smaller.

14. (original) A semiconductor device to be used for a CMOS inverter circuit, the
 semiconductor device comprising:

a dielectric film formed on a semiconductor substrate;
 a SOI film comprising single crystal Si formed on the dielectric layer film;
 a gate dielectric film formed on the SOI film;
 a gate electrode formed on the gate dielectric film; and
 a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
 wherein, when a power supply voltage of 1.0 V is used,

a thickness of the SOI film is $0.072\text{ }\mu\text{m}$ or greater and $0.082\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $1.095 \times 10^{18}/\text{cm}^3$ or greater and $1.105 \times 10^{18}/\text{cm}^3$ or smaller.

15. (original) A semiconductor device to be used for a CMOS inverter circuit, the semiconductor device comprising:

- a dielectric film formed on a semiconductor substrate;
 - a SOI film comprising single crystal Si formed on the dielectric layer film;
 - a gate dielectric film formed on the SOI film;
 - a gate electrode formed on the gate dielectric film; and
 - a diffusion layer for source/drain regions formed in source/drain regions of the SOI film,
- wherein, when a power supply voltage of 1.0 V is used,

a thickness of the SOI film is $0.076\text{ }\mu\text{m}$ or greater and $0.086\text{ }\mu\text{m}$ or smaller, and an impurity concentration of the SOI film is $1.195 \times 10^{18}/\text{cm}^3$ or greater and $1.205 \times 10^{18}/\text{cm}^3$ or smaller.

16. (new) A semiconductor device as in claim 1, further comprising first and second low concentration diffusion regions in contact with source/drain regions, the first and second low concentration diffusion regions having a lower impurity concentration than the source/drain regions, wherein a portion of each of the low concentration diffusion regions extends under the gate electrode.